




















plastic recycling

melting temperatures – working with plasticpreneur machines

CODE	DESIGNATION	MELTING TEMPERATURE	YES / NO
 PET	POLYETHYLENE TEREPHTHALATE		
 PE-HD	POLYETHYLENE HIGH-DENSITY	200-240 °C	
 PVC			
 PE-LD	POLYETHYLENE LOW-DENSITY	200-240 °C	
 PP	POLYPROPYLENE	220-250 °C	
 PS	POLYSTYRENE	220-250 °C	
 O	OTHERS		
 PLA	POLYLACTIC ACID	200-230 °C	
 ABS	ACRYLONITRILE BUTADIENE STYRENE	230-260 °C	
 TPU	THERMOPLASTIC POLYURETHANE	210-250 °C	